



# Polypropylene BorECO™ BA2000

High stiff Polypropylene Copolymer for Non-Pressure Pipes

## Description

**BorECO™ BA2000** is a high molecular weight, low melt flow rate polypropylene block copolymer with a good balance of mechanical properties. This grade offers superior stiffness while keeping good impact resistance and shows excellent processability.

## Applications

**BorECO™ BA2000** is recommended for solid wall and structured wall non-pressure gravity pipes in the application field of:

Underground drainage	Soil
Sewerage	Waste

## Physical Properties

Property	Typical Value	Test Method
<small>Data should not be used for specification work</small>		
Melt Flow Rate (230 °C/2,16 kg)	0,25 g/10min	ISO 1133
Flexural Modulus	2.000 MPa	ISO 178
Tensile Strain at Yield (50 mm/min)	6,5 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	36 MPa	ISO 527-2
Charpy Impact Strength, notched (23 °C)	30 kJ/m <sup>2</sup>	ISO 179-1
Charpy Impact Strength, notched (-20 °C)	2 kJ/m <sup>2</sup>	ISO 179-1

## Processing Techniques

The actual conditions will depend on the type of equipment used. They will also depend on size and wall thickness of the pipe produced.

Following parameters should be used as guidelines:

Cylinder	200 - 220 °C
Head	210 - 220 °C
Die	210 - 220 °C
Melt temperature	210 - 230 °C

Specific recommendations for processing conditions can be determined only when the application and type of equipment are known. Please contact your local Borealis representative for such particulars.

## Storage

**BorECO™ BA2000** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

## Safety

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

BorECO is a trademark of the Borealis group.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria  
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333  
FN 269858a | CCC Commercial Court of Vienna | Website [www.borealisgroup.com](http://www.borealisgroup.com)



**Polypropylene**  
**BorECO™ BA2000**

**Recycling**

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

**Related Documents**

For general and grade specific compliance documents please see Borealis' homepage [www.borealisgroup.com](http://www.borealisgroup.com) or ask your Borealis representative.

**Issuer:**

Product Management / Petar Doshev  
Marketing Oil & Gas / Thierry Pezard

**Disclaimer**

**The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.**

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

**Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.**

**It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.**

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.