

Polypropylene

BorECO™ BC212IM

Polypropylene Block Copolymer for Pipe Applications

Description

BorECO™ BC212IM is a polypropylene block copolymer combining high stiffness and good flowability. Its excellent stabilisation package provides improved thermal stability compared with standard injection moulding grades.

Applications

BorECO™ BC212IM is intended for injection moulding, especially in the field of stormwater boxes, sewage and underground drainage systems.

Physical properties

Property	Typical value *	Unit	Test method
Flexural modulus	1800	MPa	ISO 178
Melt flow rate (230 °C/2.16 kg)	4.5	g/10min	ISO 1133-1
Charpy impact strength, notched (-20 °C)	3.5	kJ/m²	ISO 179-1/1eA
Charpy impact strength, notched (23 °C)	8	kJ/m²	ISO 179-1/1eA
Tensile strain at yield (50 mm/min)	4	%	ISO 527-2
Tensile stress at yield (50 mm/min)	32	MPa	ISO 527-2

* Data should not be used for specification work

Processing techniques

This product is easy to process with standard injection moulding machines.

Specific recommendations for processing conditions can be determined only when the application and type of equipment are known. Please contact your local Borealis representative for such particulars.

Packaging and storage

BorECO™ BC212IM should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which can result in odour generation and colour changes and can have negative effects on the physical properties of this product.

Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency.

Further information on sustainability and Design for Recycling (DfR) can be found from our websites www.borealisgroup.com and www.borealiseverminds.com.

BorECO™ is a trademark of the Borealis Group



Polypropylene

BorECO™ BC212IM

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.