PRODUCT DATA SHEET

Post-Consumer Recyclate

Recleo™ S D7000-95

Recycled PP/PE Blend

Description

Recleo™ S D7000-95 is a black polypropylene dominated polyolefin post-consumer recyclate including a large part of recycled post-consumer waste coming from pre-sorted household waste.
Recyclass certificate is available on the webpage and upon request. Due to the nature of our recycling process, some variation can be observed between batches.
The material is supplied in pelet form.

Recleo™ S D7000-95 contains:

Typical characteristics

Good demoulding properties

Good stiffness impact balance

Available in homogenised 24-ton truckloads

Applications

Recleo™ S D7000-95 is intended for following applications:

Injection moulding non-food applications

This product is recommended for Hot Runners.

Physical properties

Property	Typical value *	Unit	Test method
Density	930	kg/m³	ISO 1183
Melt flow rate (230 °C/2.16 kg)	9	g/10min	ISO 1133
Ash 650°C [1]	<5	%	ISO 1172
Moisture content	<0.1	%	Moisture analyzer (infrared)
Tensile modulus (1 mm/min)	1000	MPa	ISO 527-2
Charpy impact strength, notched (23 °C)	5.5	kJ/m²	ISO 179-1/1eA

* Data should not be used for specification work

[1] *Refers to filler content*

Processing techniques

Following parameters should be used as a guideline:

Processing setting	Typical value/range
Melt temperature [2]	230 °C
Holding pressure [3]	350 bar
Mould temperature [4]	35 °C

Recleo™ is a trademark of the Borealis Group

Post-Consumer Recyclate

Recleo™ S D7000-95

[2]*range: 210 - 260 °C*

[3]*range: 200 - 500 bar*

[4]*range: 30 - 40 °C*

Injection speed: High
Shrinkage 1 - 2 %, depending on wall thickness and moulding parameters

Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency. Further information on sustainability and Design for Recycling (DfR) can be found from our website www.borealisgroup.com.

Disclaimer

Recycled plastics are subject to material inconsistencies. mtm/Ecoplast/Integra makes no warranties which extend beyond the description contained herein and to the best of our knowledge, the information is accurate and reliable as of the date of publication. Because of the multitude of possible influences during the use and application of our products, the information included does not release customers and users from the obligation to examine and test them carefully. Please note that nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose as mtm/Ecoplast/Integra do not know the origin of the product. Where necessary, the customer is recommended to obtain a feedstock release from the customer. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of any mtm/Ecoplast/Integra product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above. The product(s) mentioned herein are not intended to be used for food contact, drinking water contact, medical, pharmaceutical or healthcare applications and we do not support their use for such applications. Otherwise, our General Terms and Conditions of Sale apply.

Borealis GmbH | Trabrennstrasse 6-8 | A-1020 Vienna | Austria
Telephone: +43 1 22 400 0* | Fax: +43 1 22 400 333
Website www.borealisgroup.com

Recleo™ is a trademark of the Borealis Group