

Polyethylene

HE1116

Description

HE1116 is a fully formulated, ADCA (Azodicarbonamide) free, compound for physical foamed coaxial cable insulations. It is based mainly on high density polyethylene and a nucleating agent to initiate the gas injection foaming process.

Typical characteristics

HE1116 can be described with following typical characteristics:

Low attenuation over a wide range of frequencies

Broad application window

Smooth surface

Uniform cell structure

High expansion degree to slightly above 80%

No ADCA (Azodicarbonamide) in the formulation

Applications

HE1116 is intended for following applications:

Small to medium size 75 OHM coaxial cable constructions (type RG)

Specifications

ASTM D1248 Type III, Class A, Category 3, Grade E1, E3

EN 50117

EN 50290-2-37 2016

Physical properties

Property	Typical value *	Unit	Test method
Density	956	kg/m ³	ISO 1183-1/Method A
MFR 140°C/5.0kg ¹	7.2	g/10min	ISO 1133-1
Hardness, Shore D ²	61	-	ISO 868

* Data should not be used for specification work

¹ Method B

² 1 s

Electrical properties

Property	Typical value *	Unit	Test method
Dissipation factor (1 MHz)	100 x10 ⁻⁶	-	IEC 60250
Dissipation factor (1.9 GHz)	146x10 ⁻⁶	-	IEC 60250
Dielectric constant (1 MHz)	2.34	-	IEC 60250
Dielectric constant (1.9 GHz)	2.25	-	IEC 60250

* Data should not be used for specification work

Polyethylene

HE1116

Processing techniques

HE1116 can be processed over a wide range of conditions.

The construction, extruder size and setup of gas injection system all play important roles for selection of proper processing conditions including the extruder temperature profile.

At the gas injection point, a temperature of approximately 190°C. Specific recommendations for processing conditions can be determined only when the application and type of equipment are known.

Tooling

Pressure tooling is invariably required. The die diameter is a function of the level of expansion with a greater expansion requiring a smaller die. Typically a die diameter 60% of the nominal insulation outer diameter is used.

Processing setting	Typical value/range
Barrel temperature 1	115 °C
Barrel temperature 2	170 °C
Barrel temperature 3	190 °C
Barrel temperature 4	175 °C
Barrel temperature ³	175 °C
Barrel temperature ⁴	175 °C
Barrel temperature ⁵	175 °C
Adapter temperature	175 °C
Adapter temperature	180 °C
Head temperature	180 °C

³ Zone 5

⁴ Zone 6

⁵ Flange

Please contact your local Borealis representative for specific assistance

Packaging and storage

Package: Bulk, Octabins, Bags

HE1116 has a shelf life of 18 months from production date if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 30 °C (50 - 85 °F). Material shelf life is affected by the storage conditions and extreme conditions influence the general material quality and performance. It is also recommended to ensure proper stock rotation by First In – First Out principle.

Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.