

Polyethylene

NAV102

Post-Consumer Recyclate

Accelerating Action
on Circularity

Description

NAV102 is a translucent low density polyethylene post-consumer recyclate (rLDPE) supplied in pellet form for high-end blown film applications. NAV102 is an ideal LDPE used where sustainability and circularity matter. NAV102 is a 100% post-consumer recyclate including a large part of recycled post-consumer plastic waste coming from pre-sorted municipal (household) waste. NAV102 is part of the EuCertPlast certificate according to the European Standard EN 15343:2007 (certificate available upon request). Due to the nature of recyclates, some variation in colour can be observed between batches.

Typical characteristics

NAV102 can be described with following typical characteristics:

Translucent

Filtration: 100 µm

Available in homogenised 24-ton truckloads

Applications

NAV102 is intended for following applications:

- Collation shrink film
- Shrink film
- Lamination films for non-food contact primary packaging
- Non-food contact primary packaging
- Secondary and tertiary packaging where reasonable optics are needed
- Transparent bags
- Industrial packaging
- Carrier bags/light colours
- Agriculture films
- Foam Applications

Note: Minor quantity of BorShape™ LLDPE significantly boosts mechanical performances of NAV102 helping converters, brand owners and retailers meeting their sustainability goals without compromising key mechanical properties for similar packaging performance.

Physical properties

Property	Typical value *	Unit	Test method
Density	0.925	g/cm ³	ISO 1183
Melt flow rate (190 °C/2.16 kg)	0.85	g/10 min	ISO 1133-1
Bulk density	490	g/l	ISO 60
Moisture content ¹	≤ 0.05	%	

* Data should not be used for specification work

¹ internal method

Polyethylene

NAV102

Film properties

Property	Typical value *	Unit	Test method
Tensile Modulus MD	215	MPa	ISO 527-3
Tensile Modulus TD	255	MPa	ISO 527-3
Tensile strength MD	13	MPa	ISO 527-3
Tensile strength TD	15	MPa	ISO 527-3
Tensile strain at break MD	220	%	ISO 527-3
Tensile strain at break TD	255	%	ISO 527-3
Tear resistance (Elmendorf) MD	1.4	N	ISO 6383-2
Tear resistance (Elmendorf) TD	4.7	N	ISO 6383-2
Dart drop	75	g	ISO 7765-1
Haze	35	%	ASTM D1003
Gloss (45°)	30	-	ASTM D2457

* Data should not be used for specification work

Processing techniques

NAV102 is easily processed on conventional extruders.
Following extrusion parameters should be used as guideline.

Processing setting	Typical value/range
Melt temperature	160 - 190 °C

Due to differences in screw and die head designs the optimum temperature adjustments are individual and should be evaluated for each production line.

Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency.

Further information on sustainability and Design for Recycling (DfR) can be found from our websites www.borealisgroup.com and www.borealiseverminds.com.

Disclaimer

Recycled plastics are subject to material inconsistencies. mtm/Exoplast makes no warranties which extend beyond the description contained herein and to the best of our knowledge, the information is accurate and reliable as of the date of publication. Because of the multitude of possible influences during the use and application of our products, the information included does not release customers and users from the obligation to examine and test them carefully. Please note that nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose as mtm/Exoplast do not know the origin of the product. Where necessary, the customer is recommended to obtain a feedstock release from the customer. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of any mtm/Exoplast product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above. The product(s) mentioned herein are not intended to be used for food contact, drinking water contact, medical, pharmaceutical or healthcare applications and we do not support their use for such applications. Otherwise, our General Terms and Conditions of Sale apply.