## **PRODUCT DATA SHEET**

# **Post-Consumer Recyclate**

# **NAV103**

### **Polyethylene**

# EverMinds\* Accelerating Action on Circularity

#### **Description**

NAV103 is a mixed-colored low density polyethylene post-consumer recyclate (rLDPE) supplied in pellet form for blown film applications. NAV103 is an ideal LDPE used where sustainability and circularity matter. NAV103 is a post-consumer recyclate including a large part of recycled post-consumer plastic waste coming from pre-sorted municipal (household) waste. NAV103 is part of the RecyClass certificate.

Due to the nature of recyclates, some variation in color can be observed between batches.

Cas No. 9002-88-4

#### **Typical characteristics**

NAV103 can be described with following typical characteristics:

Mixed-coloured Filtration: 100 μm

Available in homogenized 24-ton truckloads

#### **Applications**

NAV103 is intended for following applications:

- Garbage bags
- Construction films
- Industrial films

#### **Physical properties**

Property	Typical value *	Unit	Test method
Density	0.945	g/cm³	ISO 1183-1
Melt flow rate (190 °C/2.16 kg)	0.7	g/10 min	ISO 1133-1
Bulk density	500	g/l	ISO 60
Moisture content <sup>1</sup>	≤ 0.06	%	
Tensile Modulus MD	240	MPa	ISO 527-3
Tensile Modulus TD	265	MPa	ISO 527-3
Tensile strength MD	12	MPa	ISO 527-3
Tensile strength TD	12	MPa	ISO 527-3
Tensile strain at break MD	230	%	ISO 527-3
Tensile strain at break TD	410	%	ISO 527-3
Tear resistance (Elmendorf) MD	1.3	N	ISO 6383-2
Tear resistance (Elmendorf) TD	5.5	N	ISO 6383-2
Dart drop	35	g * Data s	ISO 7765-1 hould not be used for specification work

<sup>&</sup>lt;sup>1</sup> internal method

Film properties measured on 40  $\mu$ m thick blown film produced on 30 mm Collin extruder L/D = 30, die diameter 60 mm, blow up ratio (BUR) = 2.5:1, frost line height (FLH) = 2D.

#### **Processing techniques**

NAV103 is easily processed on conventional extruders. Following extrusion parameters should be used as guideline:





# **Post-Consumer Recyclate**

## **NAV103**

Processing setting	Typical value/range	
Melt temperature	160 - 190 °C	

Due to differences in screw and die head designs the optimum temperature adjustments are individual and should be evaluated for each production line.

#### Packaging and storage

NAV103 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which can result in odor generation and color changes and can have negative effects on the physical properties of this product. The shelf life is a maximum of one year after production. It can be extended after selected material properties are being retested to meet the product specifications. It is recommended to measure the moisture after longer storage periods prior to processing.

#### **Product compliance documents**

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

#### Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency.

Further information on sustainability and Design for Recycling (DfR) can be found from our websites www.borealisgroup.com and www.borealiseverminds.com.

#### **Disclaimer**

Recycled plastics are subject to material inconsistencies. mtm/Ecoplast makes no warranties which extend beyond the description contained herein and to the best of our knowledge, the information is accurate and reliable as of the date of publication. Because of the multitude of possible influences during the use and application of our products, the information included does not release customers and users from the obligation to examine and test them carefully. Please note that nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose as mtm/Ecoplast do not know the origin of the product. Where necessary, the customer is recommended to obtain a feedstock release from the customer. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of any mtm/Ecoplast product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above. The product(s) mentioned herein are not intended to be used for food contact, drinking water contact, medical, pharmaceutical or healthcare applications and we do not support their use for such applications. Otherwise, our General Terms and Conditions of Sale apply.





