

Polypropylene

RE239CF

Polypropylene Random Copolymer

Description

RE239CF is a random copolymer

This grade is suitable for the manufacturing of unoriented films on chill roll processes.

Cas No. 9010-79-1

RE239CF contains:

1800	ppm	Antiblock (SiO ₂)
2000	ppm	Slip (EAA)
yes		Calcium stearate

Typical characteristics

RE239CF can be described with following typical characteristics:

Low seal initiation temperature	High tenacity
High softness and tenacity	

Applications

RE239CF is intended for following applications:

Food packaging	Stationery film
Lamination film	Flower packaging
Textile packaging film	

Physical properties

Property	Typical value *	Unit	Test method
Melt flow rate (230 °C/2.16 kg)	11	g/10min	ISO 1133-1
Flexural modulus ¹	650	MPa	ISO 178
Charpy impact strength, notched (23 °C)	6	kJ/m ²	ISO 179-1/1eA
Melting temperature	141	°C	ISO 11357-3
Vicat softening temperature A50 (10 N)	125	°C	ISO 306

¹ Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.

* Data should not be used for specification work

Packaging and storage

RE239CF should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which can result in odour generation and colour changes and can have negative effects on the physical properties of this product.

Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

Polypropylene

RE239CF

Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency. Further information on sustainability and Design for Recycling (DfR) can be found from our websites www.borealisgroup.com and www.borealiseverminds.com.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.