

## Polypropylene

# RH414FB

### Polypropylene Random Copolymer

#### Description

RH414FB is a polypropylene random copolymer targeting spunbonded high loft and soft applications. RH414FB is anti-gasfading stabilised and contains slip agent.

Cas No. 9010-79-1

#### Typical characteristics

RH414FB can be described with following typical characteristics:

Easy Processability	Controlled rheology
Optimal product consistency	Anti-gasfading stabilisation
Very good flow	Softness

#### Applications

RH414FB is intended for following applications:

Partially Oriented Yarn	Spunbonded nonwoven
Spunbonded Bi-component	
High loft for softness	

#### Physical properties

Property	Typical value *	Unit	Test method
MFR 230°C/2.16kg	35	g/10min	ISO 1133-1
Molecular weight distribution	Very narrow	-	
Melting temperature	151.0	°C	ISO 11357-3

\* Data should not be used for specification work

#### Processing techniques

The actual conditions will depend on the type of equipment used.

#### Packaging and storage

RH414FB should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which can result in odour generation and colour changes and can have negative effects on the physical properties of this product.

#### Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website [www.borealisgroup.com](http://www.borealisgroup.com).

#### Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency.

Further information on sustainability and Design for Recycling (DfR) can be found from our websites [www.borealisgroup.com](http://www.borealisgroup.com) and [www.borealiseverminds.com](http://www.borealiseverminds.com).

# Polypropylene

## RH414FB

### Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.