## **PRODUCT DATA SHEET**

**Post-Consumer Recyclate** 

# Dipolen<sup>™</sup> SP-74

### **Recycled PP/PE Blend**

#### **Description**

Dipolen<sup>™</sup> SP-74 is a dark grey polypropylene dominated polyolefin post-consumer recyclate supplied in pellets. This product is an ideal PP used where sustainability and circularity matter. Dipolen<sup>™</sup> SP-74 is a post-consumer recyclate including a large part of recycled post-consumer waste coming from pre-sorted household waste. It is a part of EuCertPlast certificate according to European Standard EN15343:2007 (certificate available upon request). Due to the nature of recyclates, some variation in colour can be observed between batches.

Good demoulding properties Good stiffness impact balance Available in homogenised 24-ton truckloads Filtration: 180µm

### Applications

Dipolen<sup>™</sup> SP-74 is intended for following applications:

Injection moulding non-food applications

### Physical properties

Property	Typical value *	Unit	Test method
Density	930	kg/m³	ISO 1183
Melt flow rate (230 °C/2.16 kg)	8	g/10min	ISO 1133
Ash content (950°C) <sup>1</sup>	<5	%	ISO 1172
Moisture content	<0.1	%	Moisture analyzer (infrared)
Tensile modulus (1 mm/min)	950	MPa	ISO 527-2
Tensile stress at yield (50 mm/min)	22	MPa	ISO 527-2
Charpy impact strength, notched (23 °C)	5	kJ/m² * Data :	ISO 179-1/1eA should not be used for specification work

<sup>2</sup> Refers to filler content

#### **Processing techniques**

Following parameters should be used as a guideline:

Processing setting	Typical value/range
Melt temperature <sup>3</sup>	230 °C
Holding pressure <sup>4</sup>	350 bar
Mould temperature <sup>5</sup>	35 °C

<sup>3</sup> range: 210 - 260 °C

<sup>4</sup> range: 200 - 500 bar

<sup>5</sup> range: 30 - 40 °C

Injection speed: High

Shrinkage 1 - 2 %, depending on wall thickness and moulding parameters









# Post-Consumer Recyclate Dipolen™ SP-74

#### Packaging and storage

Dipolen<sup>™</sup> SP-74 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which can result in odor generation and color changes and can have negative effects on the physical properties of this product. The shelf life is a maximum of one year after production. The shelf life of a product can be extended after properties are re-testing selected material properties and verifying that the test results are still within the product specification. It is recommended to measure the moisture after longer storage periods prior to processing.

#### **Product compliance documents**

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

#### Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency.

Further information on sustainability and Design for Recycling (DfR) can be found from our websites www.borealisgroup.com and www.borealiseverminds.com.

#### Disclaimer

Recycled plastics are subject to material inconsistencies. mtm/Ecoplast makes no warranties which extend beyond the description contained herein and to the best of our knowledge, the information is accurate and reliable as of the date of publication. Because of the multitude of possible influences during the use and application of our products, the information included does not release customers and users from the obligation to examine and test them carefully. Please note that nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose as mtm/Ecoplast do not know the origin of the product. Where necessary, the customer is recommended to obtain a feedstock release from the customer. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of any mtm/Ecoplast product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above. The product (s) mentioned herein are not intended to be used for food contact, drinking water contact, medical, pharmaceutical or healthcare applications and we do not support their use for such applications. Otherwise, our General Terms and Conditions of Sale apply.

mtm plastics GmbH | Bahnhofstraße 106 | D-99759 Niedergebra | Germany Tel. +49 (0) 36338 / 325-0 | Fax +49 (0) 36338 / 325-25 Website info@mtm-plastics.eu | www.mtm-plastics.eu



Dipolen<sup>™</sup> is a trademark of the Borealis Group

