

Post-Consumer Recyclate

Recleo" PE T2006

Low Density Polyethylene



Accelerating Action
on Circularity

Description

Recleo PE T2006 is a translucent low density polyethylene post-consumer recyclate (rLDPE) supplied in pellet form for high-end blown film applications. PE T2006 is an ideal LDPE used where sustainability and circularity matter. PE T2006 is a 100% post-consumer recyclate including a large part of recycled post-consumer plastic waste coming from pre-sorted municipal (household) waste. PE T2006 is part of the RecyClass certificate. Due to the nature of recyclates, some variation in color can be observed between batches.

Typical characteristics

Recleo" PE T2006 can be described with following typical characteristics:

Translucent

Filtration: 100 µm

Available in homogeniszd 24-ton truckloads

Applications

Recleo" PE T2006 is intended for following applications:

- Collation shrink film, shrink film and lamination films for non-food contact applications
- Packaging where reasonable optics are needed
- Transparent bags
- Industrial packaging
- Carrier bags/light colors
- Agriculture films

Note: Minor quantity of BorShape" LLDPE significantly boosts mechanical performances of Recleo PE T2006 helping convertors, brand owners and retailers meeting their sustainability goals without compromising key mechanical properties for similar packaging performance.

Physical properties

Property	Typical value *	Unit	Test method
Density	0.925	g/cm ³	ISO 1183
Melt flow rate (190 °C/2.16 kg)	0.85	g/10 min	ISO 1133-1
Bulk density	490	g/l	ISO 60
Moisture content ¹	d 0.1	%	

* Data should not be used for specification work

¹ internal method

Recleo" is a trademark of the Borealis Group

Post-Consumer Recyclate

Recleo" PE T2006

Film properties

Property	Typical value *	Unit	Test method
Tensile Modulus MD	215	MPa	ISO 527-3
Tensile Modulus MD	255	MPa	ISO 527-3
Tensile strength MD	13	MPa	ISO 527-3
Tensile strength TD	15	MPa	ISO 527-3
Tensile strain at break MD	220	%	ISO 527-3
Tensile strain at break TD	255	%	ISO 527-3
Tear resistance (Elmendorf) MD	1.4	N	ISO 6383-2
Tear resistance (Elmendorf) TD	4.7	N	ISO 6383-2
Dart drop	75	g	ISO 7765-1
Haze	35	%	ASTM D1003
Gloss (45°)	30	-	ASTM D2457

* Data should not be used for specification work

Film properties measured on 40 µm thick blown film produced on 30 mm Collin extruder L/D = 30, die diameter 60 mm, blow up ratio (BUR) = 2.5:1, frost line height (FLH) = 2D.

Processing setting	Typical value/range
Melt temperature	160 - 190 °C

Due to differences in screw and die head designs the optimum temperature adjustments are individual and should be evaluated for each production line.

Processing techniques

Recleo PE T2006 is easily processed on conventional extruders. Following extrusion parameters should be used as guideline.

Packaging and storage

Recleo" PE T2006 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which can result in odor generation and color changes and can have negative effects on the physical properties of this product. The shelf life is a maximum of one year after production. It can be extended after selected material properties are being retested to meet the product specifications. It is recommended to measure the moisture after longer storage periods prior to processing.

Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency.

Further information on sustainability and Design for Recycling (DfR) can be found from our websites www.borealisgroup.com and www.borealiseverminds.com.

Recleo" is a trademark of the Borealis Group

Post-Consumer Recyclate

Recleo" PE T2006

Disclaimer

Recycled plastics are subject to material inconsistencies. mtm/Ecoplast makes no warranties which extend beyond the description contained herein and to the best of our knowledge, the information is accurate and reliable as of the date of publication. Because of the multitude of possible influences during the use and application of our products, the information included does not release customers and users from the obligation to examine and test them carefully. Please note that nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose as mtm/Ecoplast do not know the origin of the product. Where necessary, the customer is recommended to obtain a feedstock release from the customer. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of any mtm/Ecoplast product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above. The product(s) mentioned herein are not intended to be used for food contact, drinking water contact, medical, pharmaceutical or healthcare applications and we do not support their use for such applications. Otherwise, our General Terms and Conditions of Sale apply.