

## Polypropylene

# Daploy™ WE100HMS

### Description

Daploy™ WE100HMS is a structurally isomeric modified propylene homopolymer intended for extrusion coating and as PP coating grade modifier to improve processing and reduce neck-in

Cas No. 9003-07-0

### Typical characteristics

Daploy™ WE100HMS can be described with following typical characteristics:

Combination of high strength and drawability in the melt phase	Excellent processing properties
Improved drawability	High temperature resistance

### Applications

Daploy™ WE100HMS is intended for following applications:

Extrusion coating and lamination

### Physical properties

Property	Typical value *	Unit	Test method
Density	910	kg/m³	ISO 1183-1
Melt flow rate (230 °C/2.16 kg)	10	g/10min	ISO 1133-1
Melting temperature	162	°C	ISO 11357-3
Vicat softening temperature A50 (10 N)	155	°C	ISO 306

\* Data should not be used for specification work

### Packaging and storage

Daploy™ WE100HMS should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which can result in odour generation and colour changes and can have negative effects on the physical properties of this product.

### Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website [www.borealisgroup.com](http://www.borealisgroup.com).

### Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency.

Further information on sustainability and Design for Recycling (DfR) can be found from our websites [www.borealisgroup.com](http://www.borealisgroup.com) and [www.borealiseverminds.com](http://www.borealiseverminds.com).

Daploy™ is a trademark of the Borealis Group



Polypropylene

## Daploy™ WE100HMS

### Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.