

## PP/PE Compound

## WE150CF

## Peelable grade for film extrusion

## Description

WE150CF is a polyolefin resin suitable for the manufacturing of non-oriented sterilisable peelable cast films on chill roll processes.

Cas No. 9010-79-1, 25087-34-7

WE150CF contains:

1000	ppm	Antiblocking agent
1100	ppm	Slip agent
yes		Calcium stearate

## Typical characteristics

WE150CF can be described with following typical characteristics:

Seal- and peelable against itself	Sterilisable
Seal- and peelable against Polypropylene	High peel force

## Applications

WE150CF is intended for following applications:

Lidding film	Medical devices
Retort food packaging	Packaging for pharmaceutical, medical device & diagnostic products
Lamination film	

For any other potential Healthcare application or end use please contact up-front your Borealis Sales Manager or Application Development Engineer.

## Physical properties

Property	Typical value *	Unit	Test method
Density	925	kg/m <sup>3</sup>	ISO 1183
Melt flow rate (230 °C/2.16 kg)	12.5	g/10min	ISO 1133-1
Flexural modulus <sup>1</sup>	1000	MPa	ISO 178
Melting temperature	135 - 155	°C	ISO 11357-3

\* Data should not be used for specification work

<sup>2</sup> Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.

## Packaging and storage

WE150CF should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which can result in odour generation and colour changes and can have negative effects on the physical properties of this product.

## Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website [www.borealisgroup.com](http://www.borealisgroup.com).

## PP/PE Compound

### WE150CF

#### Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency. Further information on sustainability and Design for Recycling (DfR) can be found from our websites [www.borealisgroup.com](http://www.borealisgroup.com) and [www.borealiseverminds.com](http://www.borealiseverminds.com).

#### Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.