

Thermoplastic Semiconductive Compound

Description

Borlink LE0315-99 has the same melt flow properties as the peroxide containing material.

Application:

LE0315-99 is used during start up of a triple-head line. It helps to use a non-peroxide-containing material until stable conditions are reached. The settings should be the same as for the peroxide containing compound.

Physical Properties

Property	Typical Value Test Method Data should not be used for specification work
Density	1170 kg/m³ ASTM D 792
Bulk density	500 - 600 kg/m³

Electrical Properties

Property	Typical Value Test Method Data should not be used for specification work		
DC Volume Resistivity (23 °C) DC Volume Resistivity (90 °C)	50 Ωcm 90 Ωcm	ASTM D 991 ASTM D 991	

Packaging

Package: Smallbins

Storage

Borlink LE0315-99 has a shelf life of 24 months after manufacturing if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 30 °C (50 - 85 °F). It is suggested that first-in/first-out practices be followed.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

Borlink is a trademark of the Borealis group.





Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

