



Polyethylene
Borlink™ LE0520-99
Thermoplastic Semiconductive Compound

Description

Borlink LE0520-99 has the same melt flow properties as the peroxide containing material.

Applications

Borlink LE0520-99 is used during start up of a triple-head line. It helps to use a non-peroxide-containing material until stable conditions are reached. The settings should be the same as for the peroxide containing compound.

Physical Properties

Property	Typical Value	Test Method
	Data should not be used for specification work	
Density	1170 kg/m ³	ASTM D 792

Electrical Properties

Property	Typical Value	Test Method
	Data should not be used for specification work	
DC Volume Resistivity (23 °C)	200 Ωcm	ASTM D 991

Packaging

Package: Smallbins

Storage

Borlink LE0520-99 has a shelf life of 24 months after manufacturing if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 30 °C (50 - 85 °F).

Borlink is a trademark of the Borealis group.

Borealis Compounds Inc | 176 Thomas Road | Port Murray, NJ 07865 | United States of America
Tel. +1 908 850 6200 | Fax +1 908 850 6268
22-2768116 | Court of New Jersey | Website www.borealisgroup.com



Polyethylene
Borlink LE0520-99

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.