



Polyethylene Borlink™ LE4244S

Crosslinkable Insulation Compound

Description

Borlink LE4244S is a crosslinkable natural polyethylene compound, specially designed for insulation of power cables.

Applications

Borlink LE4244S is intended for insulation of XLPE high voltage (HV) AC cables with rated voltages up to 230 kV ($U_m = 245$ kV).

The values are voltages between phases as defined in IEC 60183.

Specifications

Borlink LE4244S is expected to meet the applicable requirements included in the below mentioned standards provided it is processed using sound material handling, extrusion and crosslinking practices as well as appropriate testing procedures. This applies up to the maximum recommended voltage level indicated in "Applications" section above since some standards cover wider voltage ranges.

IEC 62067
IEC 60840
AEIC CS9
AEIC CS8
ANSI/ICEA S-108-720

ANSI/ICEA S-93-639
ANSI/ICEA S-94-649
ANSI/ICEA S-97-682
Cenelec HD 632 S1
UL 1072

Special Features

Borlink LE4244S is a ready-to-use natural compound. The cleanliness and product consistency of Borlink LE4244S results in a superclean insulation. Borlink LE4244S cleanliness level is assured through the Borealis quality management system. Borlink LE4244S has very low sagging properties and is specially designed for extrusion on horizontal lines and for cables with thick insulation walls extruded on CCV lines.

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density (Base Resin)	922 kg/m ³	ISO 1183
Melt Flow Rate (190 °C/2,16 kg) ¹	0,8 g/10min	ISO 1133
Tensile Strain at Break (250 mm/min) ²	> 450 %	ISO 527
Tensile Strength (250 mm/min) ²	> 17 MPa	ISO 527
Change of Tensile Properties After Ageing (168 h, 135 °C) ²	< 20 %	IEC 60811-401
Hot Set Test (200 °C, 0,20 MPa) ²	Elongation under load 75 % Permanent deformation 5 %	IEC 60811-507
MDR, max torque	3,1 - 4,5 dNm	ISO 6502
Methanol Wash ³	< 1.000 ppm	BTM 00118
Moisture	< 200 ppm	ISO 15512

¹ Base Resin

Borlink is a trademark of the Borealis group.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com



Polyethylene Borlink LE4244S

² Measured on crosslinked specimens³ BTM = Borealis Test Method

Electrical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Dielectric constant (50 Hz)	2,3	IEC 60250
DC Volume Resistivity (23 °C)	> 10 PΩcm	IEC 62631
Dissipation Factor (50 Hz)	0,0003	IEC 60250

Processing Techniques

To produce a good and reliable cable, it is essential to ensure careful and very clean handling of the insulation material. Hence all material handling should preferably be conducted in closed systems and in clean room conditions. Please contact your Borealis representative for more details.

Extrusion

A screen-pack on the extruder is recommended for improved melt homogenisation.

Melt temperature 125 - 135 °C

Packaging

Package: Octabins

Storage

Borlink LE4244S has a shelf life of 12 months from production date if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 35°C (50 - 95°F).

The material can be stored at ambient temperature up to 40°C (104°F) for a period up to 6 months provided it is in unopened original packages and under dry and clean conditions. Material shelf life is affected by the storage conditions and extreme conditions influence the general material quality and performance.

Before use, material shall be conditioned indoors (production room) to reach ambient temperature. It is also recommended to ensure proper stock rotation by First In – First Out principle.

More information on storage is found in the Safety data sheet (SDS) / Product safety information sheet (PSIS) for this product.



Polyethylene

Borlink LE4244S

Safety

Please see the Safety data sheet (SDS) / Product safety information sheet (PSIS) for details on various aspects of safety, recovery and disposal of the products. For more information, contact your Borealis representative.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.