

Polyethylene

BorSafe™ HE3492-LS-H

Orange PE100 High Density Polyethylene compound for pressure pipes

Description

BorSafe HE3492-LS-H is a bimodal polyethylene compound produced by the advanced Borstar technology.

It is a ready made compound, including a carefully selected combination of pigments and stabilizers to ensure excellent long-term thermal stability and UV-resistance for limited outdoors storage of the final product.

BorSafe HE3492-LS-H is classified as an MRS 10.0 material (PE100) and is PE100-RC classified following the draft EN/ISO PE pressure pipe standards as currently revised.

Furthermore, it has a pigment system that gives a bright colored stripe, even when extruded as a thin layer on a black pipe.

Applications

BorSafe™ HE3492-LS-H is intended for following applications:

- | | |
|---|----------------|
| Co-extrusion of layers for pressure pipes | Natural gas |
| Gas distribution | Pressure pipes |

Specifications

BorSafe™ HE3492-LS-H is expected to meet the applicable requirements included in the below mentioned standards provided it is processed using sound material handling and processing practices as well as appropriate testing procedures.

- | | |
|---------|----------|
| EN 1555 | ISO 4437 |
|---------|----------|

BorSafe HE3492-LS-H offers outstanding extrudability and good melt strength, thanks to the molecular structure, thus supporting a problem-free extrusion process to tight tolerances. The product is a high-density hexene copolymer compound with an outstanding resistance to slow crack growth and used for non-conventional pipe installation technologies, like No Dig. It shows excellent resistance to rapid crack propagation.

BorSafe HE3492-LS-H is also recommended to extrude identification stripes onto black pipes produced from BorSafe materials. As the material is already a documented pressure pipe material, it also fulfills the requirements for a stripe compound according to EN 1555-2 and ISO 4437-2.

The orange colour is similar to colour code RAL 1033.

BorSafe™ is a trademark of the Borealis Group



Polyethylene

BorSafe™ HE3492-LS-H

Physical properties

Property	Typical value *	Unit	Test method
Density	951.0	kg/m ³	ISO 1183-1/Method A
Melt flow rate (190 °C/5 kg)	0.25	g/10min	ISO 1133-1
Tensile modulus (1 mm/min)	1000	MPa	ISO 527-2
Tensile strain at break (50 mm/min)	> 600	%	ISO 527-2
Tensile stress at yield (50 mm/min)	24	MPa	ISO 527-2
Pigment dispersion	≤ 3	-	ISO 18553
Oxidation induction time (210 °C)	≥ 20	min	ISO 11357-6
Resistance to rapid crack propagation (S4 test, Pc at 0°C, Test pipe 250mm, SDR11)	> 10	bar	ISO 13477
Strain Hardening Modulus Test (SHT)	≥ 65	MPa	ISO 18488
Accelerated Full Notch Creep Test (AFNCT) in 2% Dehyton solution (4 MPa, 90 °C)	≥ 550	h	ISO 16770
Accelerated Notched Pipe Test (ANPT) in 2% Arkopal N-100 solution (9,2 bar, 80 °C)	≥ 300	h	ISO 13479
Cracked Round Bar (CRB) , converted to 14,0 mm and initial crack length 1,40 mm (12,5 MPa, 23°C)	≥ 1.5	Million cycles	ISO 18489
Resistance to gas condensate	pass	-	EN 1555-1
Resistance to weathering ≥7GJ/m ² , tests acc. to EN1555-1	pass	Pass	EN ISO 16871

* Data should not be used for specification work

Processing techniques

The actual conditions will depend on the type of equipment used.

Processing setting	Typical value/range
Cylinder temperature	190 - 210 °C
Head temperature	200 - 220 °C
Die temperature	200 - 210 °C
Melt temperature	190 - 220 °C

Specific recommendations for processing conditions can be determined only when the application and type of equipment are known. Please contact your local Borealis representative for such particulars.

Packaging and storage

BorSafe™ HE3492-LS-H shall be stored indoors below 50°C in unopened original packaging in clean and dry environment. It is recommended to ensure proper stock rotation by using first in - first out principle. Following afore-mentioned conditions the material can be stored for a period of up to 3 years after production. However, caution shall be taken regarding the moisture level. It is recommended to measure the moisture after longer storage periods prior to processing.

Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

BorSafe™ is a trademark of the Borealis Group



Polyethylene

BorSafe™ HE3492-LS-H

Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency.

Further information on sustainability and Design for Recycling (DfR) can be found from our websites www.borealisgroup.com and www.borealiseverminds.com.

Regional Availability

Europe

North America

South America

For information on regional availability please contact Borealis Sales Representative.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.