

Polyethylene

Casico™ FR6082

Halogen Free Flame Retardant Compound

Description

Casico FR6082 is a thermoplastic, halogen free flame retardant black jacketing compound combined with high mechanical strength, toughness and excellent extrusion properties.

Casico FR6082 contains 2,5% well dispersed furnace black of nominal particle size less than 25 nanometres in order to ensure excellent weathering resistance.

Typical characteristics

Casico FR6082 can be described with following typical characteristics:

High mechanical strength and toughness	Possibility for cable downsizing
Superb system ageing compatibility	Processability on most PVC/PE extrusion equipment
Low water permeability	No need for pre-drying
UV resistance	Excellent processing properties

Applications

Casico™ FR6082 is intended for following applications:

Jackets for energy cables

The principle feature of this compound is the high physical strength and toughness. It can be used in areas sensitive to smoke or corrosive and toxic combustion products. For most cable constructions, Casico FR6082 has sufficient flame retardancy to satisfy single wire vertical burning tests.

Specifications

Casico FR6082 is expected to meet the applicable requirements included in the below mentioned standards provided it is processed using sound material handling and processing practices as well as appropriate testing procedures.

BS 7655 LTS1-4	IEC 60502 Part 1, Type ST3, ST7
EN 50290-2-27	IEC 60502 Part 2, Type ST3, ST7
EN 50363-8 TM7	IEC 60840 Type ST3
HD 603 S1 DMO 1	IEC 60840 Type ST7
HD 620 S1 DMZ2	IEC 62067 Type ST7
HD 620 S2 DMZ 3-5	VDE 0207 Teil 24 (HM2, HM4 & HM5)
HD 632 S1, ST3, ST7	IEC 62067 Type ST3

Casico™ is a trademark of the Borealis Group

Polyethylene

Casico™ FR6082

Physical properties

Property	Typical value *	Unit	Test method
Density	1175	kg/m ³	ISO 1183-1
Melt flow rate (190 °C/2.16 kg)	0.6	g/10min	ISO 1133-1
Hardness, Shore D ¹	50	-	ISO 868
Tensile strength (50 mm/min) ²	13	MPa	ISO 527-2
Tensile strain at break (50 mm/min) ²	550	%	ISO 527-2
Change of tensile properties after ageing 110°C, 10 days ²	≤25	%	IEC 60811-401
Pressure test at high temperature (110 °C, 6h) ²	<10	%	IEC 60811-508
Tear resistance ²	13	N/mm	HD 605 S2

* Data should not be used for specification work

¹ 15s

² Measured on extruded tape

Electrical properties

Property	Typical value *	Unit	Test method
DC Volume resistivity (23°C)	>10	P&cm	IEC 62631

* Data should not be used for specification work

Other properties

Property	Typical value *	Unit	Test method
Limiting Oxygen Index ³	27	%	ISO 4589-2
Corrosivity of combustion fumes, pH	>4.3	-	IEC 60754-2
Corrosivity of combustion fumes, Conductivity	<10	µS/mm	IEC 60754-2

* Data should not be used for specification work

³ Specimen type IV, method A

Processing techniques

Most equipment designed for PVC/PE extrusion is suitable.

Using the below set temperatures, a stable extrusion process and a cable having a smooth glossy appearance can be achieved. On-size pressure or low draw down tube-on tooling is preferred. Whichever type of tooling is used, the die should preferably have a parallel land of length equal to the final cable diameter.

Processing setting	Typical value/range
Barrel temperature	160 - 170 - 180 - 190 °C
Die temperature	190 °C

The actual conditions will depend on the type of equipment used.

Casico FR6082 normally does not need pre-drying unless the material has been stored in a moist environment for a long period. In such cases drying in dehumidified air for 4 hours at 70°C will normally reduce the moisture content to an acceptable value.

Packaging and storage

Casico FR6082 should be stored indoors at temperatures between 10 - 30°C in unopened original packages in clean and dry environment, protected from sunlight. Following above-mentioned conditions the material can be safely stored for a period of up to 24 months after date of production.

Casico™ is a trademark of the Borealis Group



Polyethylene

Casico™ FR6082

Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website www.borealisgroup.com.

Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency. Further information on sustainability and Design for Recycling (DfR) can be found from our websites www.borealisgroup.com and www.borealiseverminds.com.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.