### PRODUCT DATA SHEET

### Polypropylene

# Fibremod™GD250SFB

### Polypropylene Compound, Glass Fibre Reinforced

#### **Description**

Fibremod<sup>™</sup>GD250SFB is a 26 % chemically coupled high performance glass fibre reinforced polypropylene compound intended for injection moulding.

This material shows excellent mechanical properties also at elevated temperatures.

#### **Applications**

Fibremod GD250SFB has been developed especially for the automotive industry.

Structural parts Window frames

White goods

#### **Physical Properties**

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

Property	Typical Value	Test Method	
	Data should not be used for specification work		
Density	1090 kg/m³	ISO 1183	
Melt Flow Rate (230 °C/2,16 kg)	5 g/10min	ISO 1133	
Flexural Modulus (2 mm/min)	5.600 MPa	ISO 178	
Tensile Stress at Yield (50 mm/min)	90 MPa	ISO 527-2	
Heat Deflection Temperature (1,80 MPa)	150 °C	ISO 75-2	
Charpy Impact Strength, notched (23 °C)	13 kJ/m²	ISO 179/1eA	

#### **Processing Techniques**

The actual conditions will depend on the type of equipment used.

To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 95° - 105°C. Fibremod GD250SFB is easy to process with standard injection moulding machines. Following moulding parameters should be used as quidelines:

Melt temperature	200 - 240 °C
Holding pressure	50-70% of injection
	pressure
Mould temperature	20 - 40 °C
Injection speed	Low to medium

#### Storage

**Fibremod GD250SFB** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

#### Recycling

The product is suitable for recycling using modern methods of shredding and cleaning.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

#### Regional Availability

South America

For information on regional availability please contact Borealis Sales Representative.

Fibremod is a trademark of the Borealis group.



## Polypropylene

## Fibremod GD250SFB

#### Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

