

## Polyethylene

## HE4883

## High Density Polyethylene Compound for Communication Cable Insulation

## Description

HE4883 is a fully formulated Azodicarbonamide free compound for physical foamed data cable insulation. HE4883 is a high-density polyethylene compound containing blowing agent for the production of foam or foam-skin insulation.

## Typical characteristics

HE4883 can be described with following typical characteristics:

Optimal cell structure	High process control
Smooth surface	Improved crushability
Easy extrusion	

## Applications

HE4883 is intended for following applications:

Data cables

HE4883 is expected to meet the applicable requirements included in the below mentioned standards provided it is processed using sound material handling and processing practices as well as appropriate testing procedures.

ASTM D1248 Type III, Class A, Category 3, Grade E1, E3

EN 50290-2-33

## Physical properties

Property	Typical value *	Unit	Test method
Density <sup>1</sup>	949	kg/m <sup>3</sup>	ISO 1183-1
Melt flow rate ( 140 °C/5 kg) <sup>2</sup>	3.5	g/10min	ISO 1133-1
Bulk density	500 - 600	kg/m <sup>3</sup>	
Tensile strain at break ( 25 mm/min)	600	%	ISO 527-2
Tensile strength ( 25 mm/min)	23	MPa	ISO 527-2
Brittleness temperature	< -76	°C	ISO 974
Hardness, Shore D <sup>3</sup>	61	-	ISO 868

\* Data should not be used for specification work

<sup>1</sup> Method A

<sup>2</sup> Method B

<sup>3</sup> 1 s

## Electrical properties

Property	Typical value *	Unit	Test method
Dissipation factor (1 MHz)	90 x10-6	-	IEC 60250
Dissipation factor (1.9 GHz)	175x10-6	-	IEC 60250
Dielectric constant (1 MHz)	2.33	-	IEC 60250

\* Data should not be used for specification work

# Polyethylene

## HE4883

### Processing techniques

HE4883 can be processed over a wide range of conditions. The construction, extruder size and setup of gas injection system all play important roles for selection of proper processing conditions including the extruder temperature profile. At the gas injection point, a temperature of approximately 200-210°C is recommended for optimal activation of the cell nucleating agent, which is of the Azodicarbonamide free type. Specific recommendations for processing conditions can be determined only when the application and type of equipment are known. Tooling: Pressure tooling is invariably required. The die diameter is a function of the level of expansion with a greater expansion requiring a smaller die. Typically die diameters 20 to 25% below the nominal insulation outer diameter are used.

Typical extrusion temperatures

Please contact your local Technical service responsible for recommendations for particular lines

Zone 1 160°C

Zone 2 190°C

Zone 3 210°C

Gas Injection Zone 4 210°C

Zone 5 210°C

Flange 210°C

Adapter 210°C

Head 210°C

Die 220°C

Please contact your local Borealis representative for such particulars.

### Packaging and storage

Package: Bulk, Octabins, Bags

HE4883 has a shelf life of 18 months from production date if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 30 °C (50 - 85 °F). Material shelf life is affected by the storage conditions and extreme conditions influence the general material quality and performance. It is also recommended to ensure proper stock rotation by First In – First Out principle.

### Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website [www.borealisgroup.com](http://www.borealisgroup.com).

### Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency. Further information on sustainability and Design for Recycling (DfR) can be found from our websites [www.borealisgroup.com](http://www.borealisgroup.com) and [www.borealiseverminds.com](http://www.borealiseverminds.com).

### Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.