

## Polyethylene

# LE6022

## Low Density Polyethylene Compound for Cable Jacketing

### Description

LE6022 is a black low density copolymer modified polyethylene compound.

It is characterized by excellent stress crack resistance and mechanical properties and low temperature performance in combination with good extrudability. LE6022 contains 2.5 % well dispersed furnace black in order to ensure excellent weathering resistance

### Typical characteristics

LE6022 can be described with following typical characteristics:

Excellent environmental stress cracking resistance (ESCR)	Excellent mechanical properties
Low temperature performance	Low flexural modulus

### Applications

LE6022 is intended for following applications:

Jackets for energy and communication cables

### Specifications

LE6022 is expected to meet the applicable requirements included in the below mentioned standards provided it is processed using sound material handling and processing practices as well as appropriate testing procedures.

ASTM D1248 Type I, Class C, Category 5, Grade E5, J3, W2-4	IEC 60502 Part 2, Type ST3
EN 50290-2-24	IEC 60708
HD 620 S2 Part 1, table 4B, DMP 17	IEC 60840 Type ST3

### Physical properties

Property	Typical value *	Unit	Test method
Density	931	kg/m <sup>3</sup>	ISO 1183-1
Melt flow rate ( 190 °C/2.16 kg)	0.2	g/10min	ISO 1133-1
Flexural modulus	>180	MPa	ISO 178
Base resin density	918	kg/m <sup>3</sup>	ISO 1183-1
Tensile strength ( 50 mm/min)	>15	MPa	ISO 527-2
Tensile strain at break ( 50 mm/min)	>600	%	ISO 527-2
Absorption coefficient <sup>1</sup>	≥320	-	ASTM D3349
Brittleness temperature	<-76	°C	ASTM D746
Environmental stress crack resistance ( 50°C, Igepal 10%, F20)	>1000	h	IEC 60811-406
Hardness, Shore D <sup>2</sup>	50	-	ISO 868

\* Data should not be used for specification work

<sup>1</sup> Measured at 375 nm

<sup>2</sup> 1 sec

# Polyethylene

## LE6022

### Electrical properties

Property	Typical value *	Unit	Test method
DC volume resistivity	10	PΩcm	IEC 62631
Dielectric strength	20	kV/mm	IEC 60243

\* Data should not be used for specification work

### Processing techniques

LE6022 provides excellent surface finish and high output rates over a broad range of conditions. For normal extrusion equipments and applications we suggest a melt temperature and a conductor preheating according to the table below:

Processing setting	Typical value/range
Melt temperature	200 - 210 °C

Specific recommendations for processing conditions can be determined only when the application and type of equipment are known. Please contact your Borealis representative for such particulars.

### Packaging and storage

Package: Bags, Octabins

LE6022 has a shelf life of 24 months from production date if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 30 °C (50 - 85 °F). Material shelf life is affected by the storage conditions and extreme conditions influence the general material quality and performance. It is also recommended to ensure proper stock rotation by First In – First Out principle.

### Product compliance documents

Latest versions of product safety information sheets (PSIS), product safety data sheets (SDS) and other product liability documents are available in our website [www.borealisgroup.com](http://www.borealisgroup.com).

### Sustainability aspects

Borealis is ever mindful of the impact of our products on the planet. We promote Design for Circularity (DfC) and Design for Recycling (DfR) to conserve natural resources and to reduce the environmental impact of products over their entire lifetime (including production, use phase and after phase). DfR helps ensure that material can be effectively recycled while maximizing the material performance efficiency. Further information on sustainability and Design for Recycling (DfR) can be found from our websites [www.borealisgroup.com](http://www.borealisgroup.com) and [www.borealiseverminds.com](http://www.borealiseverminds.com).

### Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.