



Polypropylene RB307MO

Description

RB307MO is a random copolymer with good transparency and contact clarity, very good gloss and surface finish. This grade also features high heat distortion temperature.

CAS-No. 9010-79-1

Applications

Household and chemical containers such as detergents,
cleaners, motor oils
Industrial chemicals

Cosmetics

Special Features

Improved gloss and excellent transparency
Good contact clarity

Optimal surface

Physical Properties

Property	Typical Value	Test Method
<small>Data should not be used for specification work</small>		
Density	905 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	1,5 g/10min	ISO 1133
Flexural Modulus	850 MPa	ISO 178
Tensile Modulus (1 mm/min)	900 MPa	ISO 527-2
Tensile Strain at Yield (50 mm/min)	13 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	24 MPa	ISO 527-2
Heat Deflection Temperature (0,45 N/mm ²)	70 °C	ISO 75-2
Charpy Impact Strength, notched (23 °C)	20 kJ/m ²	ISO 179/1eA

Processing Techniques

Following parameters should be used as guidelines:

RB307MO is easy to extrude and can be used in all conventional blow-moulding machines

Barrel	190 - 220 °C
Die	180 - 220 °C
Melt temperature	180 - 220 °C



Polypropylene RB307MO

Storage

RB307MO should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Recovery and disposal of polyolefins
"Safety data sheet" / "Product safety information sheet"
Information on emissions from processing and fires
Statement on compliance to food contact regulations
Statement on toys regulations



Polypropylene
RB307MO

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.