

## Polyethylene

# Visico™ LE0542

## Silane Crosslinkable Semiconductive Compound

### Description

Visico LE0542 is a silane crosslinkable black polyethylene compound, specially designed for semiconductive conductor screen and bonded insulation screen of power cables. It is used for co-extrusion with LDPE silane crosslinkable insulation materials.

### Applications

Visico™ LE0542 is intended for following applications:

Semiconductive screen in silane crosslinkable medium voltage ( MV) AC cables with rated voltages up to 36 kV ( Um = 42 kV) . It can be used as conductor and insulation screen for bonded cable constructions and as conductor screen for strippable cable constructions. The values are voltages between phases as defined in IEC 60183

### Specifications

IEC 60502-2

Cenelec HD 620 S2 (Part 1)

Visico LE0542 is expected to meet the applicable requirements included in the below mentioned standards provided it is processed using sound material handling, extrusion and crosslinking practices as well as appropriate testing procedures. This applies up to the maximum recommended voltage level indicated in "Applications" section above since some standards cover wider voltage ranges.

### Physical properties

Property	Typical value *	Unit	Test method
Density	1125	kg/m <sup>3</sup>	ISO 1183
Tensile strength ( 25 mm/min) <sup>1</sup>	>10	MPa	ISO 527
Tensile strain at break ( 25 mm/min) <sup>1</sup>	>150	%	ISO 527
Moisture content	200	ppm	ISO 15512
Elongation at break after ageing ( 135°C, 168h) <sup>1</sup>	>100	%	IEC 60811-401

<sup>1</sup> Measured on crosslinked specimens.

\* Data should not be used for specification work

### Electrical properties

Property	Typical value *	Unit	Test method
DC Volume resistivity (23°C) <sup>1</sup>	<100	Ωcm	ISO 3915

<sup>1</sup> Measured on crosslinked specimens.

\* Data should not be used for specification work

### Processing techniques

Visico LE0542 provides excellent surface finish and minimal risk for scorch when processing conditions are optimal. The actual conditions will depend on the type of equipment used. To produce a good and reliable cable, it is essential to ensure careful and very clean handling of the insulation material. Hence all material handling should preferably be conducted in closed systems and in clean room conditions. Please contact your Borealis representative for more details.

Visico™ is a trademark of the Borealis Group



# Polyethylene

## Visico™ LE0542

### Extrusion

A screen-pack on the extruder is recommended for improved melt homogenisation.

### Crosslinking

Visico LE0542 in combination with Visico LE4422M/Visico LE4431M shall be crosslinked by immersion in hot water or exposed to low pressure steam at a temperature in typical circumstances of 70-80 °C. The time period needed for crosslinking will depend on e.g. the thickness of insulation or reel size. It is good practice to purge stranded aluminium conductors with air or nitrogen during crosslinking to prevent conductor corrosion.

## Packaging and storage

Package: Smallbins

Visico™ LE0542 has a shelf life of 18 months from production date if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 30 °C (50 - 85 °F).

Material shelf life is affected by the storage conditions and extreme conditions influence the general material quality and performance.

It is also recommended to ensure proper stock rotation by First In – First Out principle.

More information on storage is found in the Safety data sheet (SDS) / Product safety information sheet (PSIS) for this product

### Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.